

## CASTUND

ladle well filler sand.  
High quality components.  
High performance rate: 90% free opening

### CHEMICAL SPECIFICATIONS

<b>SIO2</b>	30,7%
<b>CR2O3</b>	31,8 %
<b>AL2O3</b>	10,5 %
<b>MGO</b>	6,5%
<b>FE2O3</b>	18,4%

### PHYSICAL SPECIFICATIONS

grain size distribution:

> 1 mm	4 - 14 %
> 0.5 mm	15 - 30 %
> 0.2 mm	40 - 57 %
> 0.1 mm	10 - 25 %

bulk density: 2,48 gr/cm<sup>3</sup>

Melting point: 1.740° C

Preservation: in a dry environment with natural ventilation.

Packing: small bags 10/15 kgs each  
big bags 1000/1500 kgs each

absolutely free of any toxic substances, this composition, mainly produced with natural elements, is free of exavalent chrome (Cr6+) and does not yeld ions even if treated with water.